



# sanwil®



PRODUKTKARTE

## SKADEN B-353

Anwendung



Beschichtung - PVC	100%
Durch - PES	100%
Flächengewicht [g/m <sup>2</sup> ]	550 ± 50
Dicke [mm]	0,9 ± 0,2
Bruchkraft [daN/5cm] Methode 2 längs / quer	≥ 30 / ≥ 15
Abriebfestigkeit der Beschichtung (Martindael-Methode) [Zyklen]	≥ 30 000 (Допустимая степень повреждения 2)
Brennbarkeit	PN EN 1021-1 PN EN 1021-2



# sanwil®



PRODUKTKARTE

## SKADEN B-353



REACH



Сертификат  
Государственного  
института гигиены  
(PZH)



Не содержит фталатов



Огнестойкий



Водонепроницаемый