

## PRODUCT'S CARD

### SOFT MARINE B-544

Usage



Coating - PVC	100%
Backing - PES	100%
Weight [g/m <sup>2</sup> ]	720 ± 60
Thickness [mm]	1,1 ± 0,2
Tensile strength [daN/5cm] Method 2 along / across	≥ 30 ≥ 15
Tear strength along / across [daN]	≥ 2 ≥ 2
Adhesion of the coating - along / across [daN/5cm]	≥ 2 ≥ 2
Resistance to repeated bending at room [number of bends in thousands]	≥ 100
Abrasion resistance (Martindale Method) [cycles]	≥ 80 000
Flame retardancy	IMO FTPC Part 8



# sanwil®



PRODUCT'S CARD

## SOFT MARINE B-544



IMO



REACH



Attestation of the Polish  
Institute of Hygiene



Phthalates free



Fireproof



Resistant to UV



Salt water resistant



Resistant to scratches



Outdoor



Waterproof